

Hole Number: ES07-105

Units: METRIC

Project Name: Norway - Espedalen	Primary Coordinates Grid: UTM84-32N	Destination Coordinates Grid: UTM:	Collar Dip: -50.00
Project Number: 201	North: 6804253.60	North: 61.37	Collar Az: 230.00
Location: Trona	East: 536461.70	East: 9.68	Length: 244.01 (m)
	Elev: 855.00	Elev: 855.00	Start Depth: 0.00 (m)
Date Started: Jan 18, 2008	Collar Survey: N	Plugged: N	Contractor: Drillcon Core AB
Date Completed: Feb 02, 2008	Multishot Survey: N	Hole Size: TT46	Core Storage: Tyrstrand
Logged By: rdnor	Pulse EM Survey: N	Casing: Left in Hole	Final Depth: 244.01 (m)

Comments: Target: South Western edge of Mag anomaly and inferred contact of ultramafic body.

Results: 155-156.03 contains 90% massive sulphides, 85% Po with 3% Pn and 2% Cpy

166.75-167.06 contains 20% sulphides, 19% Po -1% Cpy and trace Pn

185.37-185.67 contains 40% sulphides, 35% Po, 3% Pn and 2% Cpy

Sample Averages

Detailed Lithology		Assay Data							
From (m)	To (m)	Lithology	Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
0	3.00	O/B, Overburden Overburden							
3.00	28.00	UM, Ultramafic Ultramafic Dark black fg homogenous pyroxenite. Competent. Barren of sulphides. Few carbonate veins and serpentine along fractured surfaces. 1-2% disseminated sulphides throughout. Mineralization 3.00 - 28.00 : PN Pentlandite, DIS Disseminated, 1% 3.00 - 28.00 : PO Pyrrhotite, DIS Disseminated, 1%	PG08198	16.30	17.00	0.70	0.1170	0.0250	0.0150
			PG08199	17.00	17.62	0.62	0.1400	0.0410	0.0150
			PG08201	17.62	19.00	1.38	0.1400	0.0350	0.0150
			PG08202	19.00	19.45	0.45	0.1120	0.0290	0.0120
			PG08203	19.45	20.45	1.00	0.1640	0.0510	0.0140
			PG08204	20.45	21.53	1.08	0.1510	0.0680	0.0120
			PG08205	21.53	22.50	0.97	0.1990	0.1000	0.0150
			PG08206	22.50	23.55	1.05	0.1820	0.0600	0.0150
			PG08207	23.55	24.53	0.98	0.1570	0.0550	0.0160
			PG08208	24.53	25.59	1.06	0.1240	0.0360	0.0150
			PG08209	25.59	26.40	0.81	0.1610	0.0370	0.0180
			PG08210	26.40	27.40	1.00	0.1680	0.0830	0.0140
			PG08211	27.40	28.55	1.15	0.1370	0.0620	0.0130

DETAILED LOG

Hole Number: ES07-105

Units: METRIC

Detailed Lithology		Lithology	Assay Data						
From (m)	To (m)		Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
28.00	62.00	GAB, Gabbro	PG08212	28.55	29.36	0.81	0.1240	0.0660	0.0110
		Gabbro	PG08213	29.36	30.28	0.92	0.1510	0.0760	0.0130
		Black to white, fg, heterogenous gabbro. Pyroxene and plag are major components. Approaching ultramafic px content in localities. From 28-38 m ~ 1% disseminated sulphides, Pn & Po 46-62m ~ 1 % diss. sulphs.	PG08214	30.28	31.28	1.00	0.0510	0.0330	0.0060
		Mineralization	PG08215	31.28	32.33	1.05	0.0470	0.0400	0.0070
		28.00 - 38.00 : PN Pentlandite, DIS Disseminated, 0.5%	PG08216	32.33	33.23	0.90	0.0840	0.0300	0.0100
		28.00 - 38.00 : PO Pyrrhotite, DIS Disseminated, 0.5%	PG08217	33.23	34.23	1.00	0.1970	0.0730	0.0160
			PG08218	34.23	35.23	1.00	0.1330	0.0790	0.0110
			PG08219	35.23	36.23	1.00	0.0820	0.0610	0.0090
			PG08221	36.23	37.23	1.00	0.1150	0.0570	0.0110
			PG08222	37.23	38.23	1.00	0.0710	0.0340	0.0080
			PG08223	38.23	39.70	1.47	0.0950	0.0430	0.0090
			PG08224	39.70	40.70	1.00	0.0200	0.0140	0.0040
			PG08225	40.70	41.70	1.00	0.0940	0.0430	0.0070
			PG08226	41.70	42.70	1.00	0.0740	0.0400	0.0060
			PG08227	42.70	43.70	1.00	0.1090	0.0580	0.0090
			PG08228	43.70	44.70	1.00	0.0720	0.0380	0.0060
			PG08229	44.70	45.70	1.00	0.0500	0.0330	0.0050
			PG08230	45.70	46.70	1.00	0.0240	0.0190	0.0040
			PG08231	46.70	47.70	1.00	0.0520	0.0430	0.0060
			PG08232	47.70	48.70	1.00	0.0470	0.0270	0.0050
			PG08233	48.70	49.70	1.00	0.0250	0.0160	0.0040
			PG08234	49.70	50.50	0.80	0.1000	0.1020	0.0070
			PG08235	50.50	51.50	1.00	0.1880	0.1170	0.0120
			PG08236	51.50	52.50	1.00	0.1680	0.0750	0.0110
			PG08237	52.50	53.50	1.00	0.2110	0.0800	0.0140
			PG08238	53.50	54.16	0.66	0.0930	0.0580	0.0070
			PG08239	54.16	55.16	1.00	0.1460	0.0690	0.0100
			PG08241	55.16	56.16	1.00	0.2630	0.0930	0.0180
			PG08242	56.16	57.00	0.84	0.1850	0.1120	0.0130
			PG08243	57.00	58.00	1.00	0.2020	0.0670	0.0140
			PG08244	58.00	59.00	1.00	0.0900	0.0480	0.0070
			PG08245	59.00	60.05	1.05	0.1140	0.0940	0.0080
			PG08246	60.05	61.05	1.00	0.1530	0.0650	0.0100
			PG08247	61.05	62.05	1.00	0.3840	0.1010	0.0260

DETAILED LOG

Hole Number: ES07-105

Units: METRIC

Detailed Lithology		Lithology	Assay Data						
From (m)	To (m)		Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
62.00	155.00	UM, Ultramafic	PG08248	62.05	63.05	1.00	0.1070	0.0810	0.0080
		Ultramafic	PG08249	63.05	64.00	0.95	0.0270	0.0180	0.0030
		Dark black fg homogenous pyroxenite. Competent. Barren of sulphides. Few carbonate veins and serpentine along fractured surfaces. Same as above ultramafic unit. Pyroxenite.	PG08250	64.00	65.00	1.00	0.1090	0.0680	0.0070
			PG08301	65.00	66.00	1.00	0.2240	0.0850	0.0140
			PG08302	66.00	67.00	1.00	0.2860	0.1150	0.0190
		From 65-87m. ~2% diss. sulphs, Po & Pn.	PG08303	67.00	68.00	1.00	0.2040	0.0680	0.0150
			PG08304	68.00	69.00	1.00	0.1400	0.0750	0.0100
		From 91-108m ~2% diss. sulphs, Po & Pn w/ trace Cpy.	PG08305	69.00	70.00	1.00	0.2080	0.0760	0.0150
			PG08306	70.00	71.00	1.00	0.2230	0.0740	0.0160
		From 115-133m ~2% diss. sulphs, Po & Pn	PG08307	71.00	72.00	1.00	0.2400	0.0750	0.0190
		Mineralization	PG08308	72.00	73.00	1.00	0.2310	0.1380	0.0150
		91.00 - 108.00 : Cpy Chalcopyrite, TR Trace, 0.5%	PG08309	73.00	74.00	1.00	0.2310	0.1650	0.0150
		115.00 - 133.00 : PN Pentlandite, DIS Disseminated, 1%	PG08310	74.00	75.00	1.00	0.2010	0.0670	0.0130
		115.00 - 133.00 : PO Pyrrhotite, DIS Disseminated, 1%	PG08311	75.00	76.00	1.00	0.1300	0.0730	0.0090
		91.00 - 108.00 : PN Pentlandite, DIS Disseminated, 1%	PG08312	76.00	77.00	1.00	0.0540	0.0780	0.0040
		91.00 - 108.00 : PO Pyrrhotite, DIS Disseminated, 1%	PG08313	77.00	78.00	1.00	0.1600	0.0690	0.0100
		65.00 - 87.00 : Cpy Chalcopyrite, TR Trace, 0.5%	PG08314	78.00	78.30	0.30	0.4920	0.3900	0.0300
		65.00 - 87.00 : PO Pyrrhotite, DIS Disseminated, 1%	PG08315	78.30	79.00	0.70	0.2230	0.0970	0.0130
		65.00 - 87.00 : PN Pentlandite, DIS Disseminated, 1%	PG08316	79.00	80.00	1.00	0.2030	0.0880	0.0120
			PG08317	80.00	81.00	1.00	0.2380	0.1570	0.0150
			PG08318	81.00	82.00	1.00	0.1320	0.0620	0.0110
			PG08319	82.00	83.00	1.00	0.2280	0.1390	0.0140
			PG08321	83.00	84.00	1.00	0.2580	0.1010	0.0160
			PG08322	84.00	85.00	1.00	0.2790	0.1490	0.0180
			PG08323	85.00	86.00	1.00	0.1830	0.0580	0.0130
			PG08324	86.00	87.00	1.00	0.1340	0.0710	0.0090
			PG08325	87.00	88.00	1.00	0.1690	0.0720	0.0100
			PG08326	88.00	89.00	1.00	0.0480	0.0350	0.0040
			PG08327	89.00	90.00	1.00	0.0470	0.0370	0.0040
			PG08328	90.00	91.00	1.00	0.1240	0.1260	0.0080
			PG08329	91.00	92.00	1.00	0.2940	0.1720	0.0170
			PG08330	92.00	93.00	1.00	0.2540	0.1150	0.0150
			PG08331	93.00	94.00	1.00	0.2590	0.1730	0.0160
			PG08332	94.00	95.00	1.00	0.2340	0.1630	0.0150
			PG08333	95.00	96.00	1.00	0.1730	0.1230	0.0120
			PG08334	96.00	97.00	1.00	0.1150	0.1160	0.0080
			PG08335	97.00	98.00	1.00	0.3530	0.2040	0.0220
			PG08336	98.00	99.00	1.00	0.2020	0.1050	0.0140
			PG08337	99.00	100.00	1.00	0.1620	0.0650	0.0120
			PG08338	100.00	101.00	1.00	0.1420	0.0860	0.0100
			PG08339	101.00	102.00	1.00	0.1670	0.0870	0.0110
			PG08341	102.00	103.00	1.00	0.2120	0.0800	0.0170
			PG08342	103.00	104.00	1.00	0.1290	0.0410	0.0140

DETAILED LOG

Hole Number: ES07-105

Units: METRIC

Detailed Lithology		Assay Data							
From (m)	To (m)	Lithology	Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
			PG08343	104.00	105.00	1.00	0.1570	0.0510	0.0160
			PG08344	105.00	106.00	1.00	0.1380	0.0470	0.0150
			PG08345	106.00	107.00	1.00	0.1230	0.0480	0.0130
			PG08346	107.00	108.00	1.00	0.2490	0.0870	0.0170
			PG08347	108.00	109.00	1.00	0.1650	0.1040	0.0120
			PG08348	109.00	110.00	1.00	0.2060	0.1120	0.0140
			PG08349	110.00	111.00	1.00	0.1220	0.0640	0.0100
			PG08350	111.00	112.00	1.00	0.1010	0.0550	0.0080
			PG08351	112.00	113.00	1.00	0.0950	0.0510	0.0080
			PG08352	113.00	114.00	1.00	0.2260	0.1020	0.0150
			PG08353	114.00	115.00	1.00	0.2470	0.1140	0.0160
			PG08354	115.00	116.00	1.00	0.2120	0.1470	0.0140
			PG08355	116.00	117.00	1.00	0.1450	0.0740	0.0110
			PG08356	117.00	118.00	1.00	0.1290	0.0760	0.0090
			PG08357	118.00	119.00	1.00	0.0660	0.0660	0.0080
			PG08358	119.00	120.00	1.00	0.0860	0.0630	0.0070
			PG08359	120.00	121.00	1.00	0.1790	0.1150	0.0130
			PG08361	121.00	122.00	1.00	0.1800	0.0690	0.0140
			PG08362	122.00	123.00	1.00	0.1240	0.0570	0.0110
			PG08363	123.00	124.00	1.00	0.1370	0.1880	0.0110
			PG08364	124.00	125.00	1.00	0.1690	0.1030	0.0120
			PG08365	125.00	126.00	1.00	0.1230	0.0560	0.0080
			PG08366	126.00	127.00	1.00	0.0940	0.0640	0.0090
			PG08367	127.00	128.00	1.00	0.1550	0.0510	0.0180
			PG08368	128.00	129.00	1.00	0.1830	0.0760	0.0200
			PG08369	129.00	130.00	1.00	0.1450	0.0490	0.0150
			PG08370	130.00	131.00	1.00	0.1620	0.0560	0.0180
			PG08371	131.00	132.00	1.00	0.1640	0.0820	0.0180
			PG08372	132.00	133.00	1.00	0.1500	0.0520	0.0180
			PG08373	133.00	134.00	1.00	0.1450	0.0440	0.0180
			PG08374	134.00	135.00	1.00	0.1420	0.0610	0.0180
			PG08375	135.00	136.00	1.00	0.0520	0.0220	0.0080
			PG08376	136.00	137.00	1.00	0.0040	0.0025	0.0030
			PG08377	137.00	138.00	1.00	0.0040	0.0025	0.0030
			PG08378	138.00	139.00	1.00	0.0030	0.0025	0.0020
			PG08379	139.00	140.00	1.00	0.0140	0.0110	0.0030
			PG08381	140.00	141.00	1.00	0.0990	0.0430	0.0070
			PG08382	141.00	142.00	1.00	0.0960	0.0510	0.0070
			PG08383	142.00	143.00	1.00	0.1270	0.0810	0.0080
			PG08384	143.00	144.00	1.00	0.1470	0.0810	0.0090
			PG08385	144.00	145.00	1.00	0.1170	0.0560	0.0080
			PG08386	145.00	146.00	1.00	0.0760	0.0350	0.0060
			PG08387	146.00	147.00	1.00	0.0780	0.0480	0.0060

Hole Number: ES07-105

Units: METRIC

Detailed Lithology		Lithology	Assay Data						
From (m)	To (m)		Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
			PG08388	147.00	148.00	1.00	0.0670	0.0340	0.0060
			PG08389	148.00	149.00	1.00	0.0270	0.0150	0.0040
			PG08390	149.00	150.00	1.00	0.0920	0.0470	0.0080
			PG08391	150.00	151.00	1.00	0.0630	0.0360	0.0060
			PG08392	151.00	152.00	1.00	0.0660	0.0310	0.0060
			PG08393	152.00	153.00	1.00	0.0980	0.0490	0.0070
			PG08394	153.00	154.00	1.00	0.0870	0.0500	0.0070
			PG08395	154.00	155.00	1.00	0.2140	0.3270	0.0150
155.00	156.03	MS, Massive Sulphide Massive Sulphides 90% sulphides consisting of 85% Po, 3% Pn and 2% Cpy. Po is massive with blebs and eyes of Pn with smaller blebs of Cpy concentrated mainly near boundaries. Host rock is small black grains with sulphide matrix, possible quartz as well. Mineralization 155.00 - 156.03 : Cpy Chalcopyrite, BL Blebby, 2% 155.00 - 156.03 : PN Pentlandite, BL Blebby, 3% 155.00 - 156.03 : PO Pyrrhotite, Mass Massive, 85%	PG08396	155.00	155.33	0.33	4.1120	0.0990	0.2520
			PG08397	155.33	155.66	0.33	3.9670	0.0840	0.2380
			PG08398	155.66	156.03	0.37	3.2530	0.5620	0.1930
156.03	162.00	GAB, Gabbro Gabbro Black to white, fg, heterogenous gabbro. Pyroxene and plag are major components. Approaching ultramafic px content in localities. Very similar to above Gabbro unit.	PG08399	156.03	157.00	0.97	0.1900	0.2430	0.0130
			PG08401	157.00	158.00	1.00	0.0190	0.0120	0.0030
162.00	173.00	UM, Ultramafic Ultramafic Black fg pyroxenite with carbonate veins along fractured surfaces along with serpentinite. Grading upper and lower contacts. 166.76-167.05 contains 20% sulphides. 19% semi-massive Po w/ 1% Cpy Trace Pn. Mineralization 166.75 - 167.06 : PN Pentlandite, TR Trace, 0.5% Trace amounts. 166.75 - 167.06 : Cpy Chalcopyrite, BL Blebby, 1% 166.75 - 167.06 : PO Pyrrhotite, SM Semi-Massive, 19%	PG08402	163.35	164.35	1.00	0.0870	0.0260	0.0130
			PG08403	164.35	165.37	1.02	0.0680	0.0110	0.0120
			PG08404	165.37	166.06	0.69	0.0740	0.0180	0.0110
			PG08405	166.06	166.75	0.69	0.0770	0.0490	0.0110
			PG08406	166.75	167.06	0.31	0.7310	0.1410	0.0580
			PG08407	167.06	168.04	0.98	0.0940	0.0180	0.0130
			PG08408	168.04	169.08	1.04	0.0860	0.0320	0.0110
			PG08409	169.08	170.05	0.97	0.1450	0.0660	0.0130
			PG08410	170.05	171.07	1.02	0.1450	0.0440	0.0140
			PG08411	171.07	172.08	1.01	0.1140	0.0290	0.0110
			PG08412	172.08	173.10	1.02	0.0850	0.0090	0.0100

Hole Number: ES07-105

Units: METRIC

Detailed Lithology		Lithology	Assay Data						
From (m)	To (m)		Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
173.00	206.00	GAB, Gabbro Gabbro Black to white, fg, heterogenous gabbro. Pyroxene and plag are major components. Approaching ultramafic px content in localities. 174-174.40 contains 10% Po 2% Pn 1% Cpy 185.37 to 185.67 contains 40% sulphides. 35% Net-Textured Po 3% Eyes Pn 2% blebby Cpy. 194.35-194.65 contains 10% sulphs, 8% net textured Po with 2% eyes of Pn Mineralization 174.00 - 174.40 : Cpy Chalcopyrite, TR Trace, 1% 174.00 - 174.40 : PN Pentlandite, E Eyes, 2% 174.00 - 174.40 : PO Pyrrhotite, BL Blebby, 10% 194.35 - 194.65 : PN Pentlandite, E Eyes, 2% eyes 194.35 - 194.65 : PO Pyrrhotite, Net Net Textured, 8% net textured 185.37 - 185.67 : Cpy Chalcopyrite, DIS Disseminated, 2% diss. flecks 185.37 - 185.67 : PN Pentlandite, DIS Disseminated, 3% diss. flecks 185.37 - 185.67 : PO Pyrrhotite, SM Semi-Massive, 35% semi-massive	PG08413	173.10	174.00	0.90	0.0930	0.0060	0.0120
			PG08414	174.00	174.40	0.40	0.3030	0.0730	0.0370
			PG08415	174.40	175.40	1.00	0.0120	0.0060	0.0040
			PG08416	184.37	185.37	1.00	0.0050	0.0025	0.0030
			PG08417	185.37	185.67	0.30	0.4220	0.4660	0.0770
			PG08418	185.67	186.67	1.00	0.0190	0.0180	0.0060
			PG08419	193.35	194.35	1.00	0.0230	0.0210	0.0050
			PG08421	194.35	194.65	0.30	0.1430	0.0610	0.0190
			PG08422	194.65	195.65	1.00	0.0260	0.0120	0.0060
206.00	225.00	UM, Ultramafic Ultramafic Black fg pyroxenite with poikoblastic texture through out. Broken and fractured surfaces have slight carbonate and chlorite alterations. Portions are highly competent.							
225.00	244.00	GNOR, Gabbro Norite Gabbro-Norite Whitish-Grey to Black, fg. Heterogenous. Texture ranges from slightly banded btw. plag and px to highly distorted fabric with no preferred alignment. Segments show plag with px interstitial. Serpentinite alteration of fractured surfaces. Footwall rock at Trona project.							
244.00	244.01	EOH, End of Hole							

Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
PG08198	16.30	17.00	0.1170	0.0250	0.0150
PG08199	17.00	17.62	0.1400	0.0410	0.0150

Hole Number: ES07-105

Units: METRIC

Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
PG08201	17.62	19.00	0.1400	0.0350	0.0150
PG08202	19.00	19.45	0.1120	0.0290	0.0120
PG08203	19.45	20.45	0.1640	0.0510	0.0140
PG08204	20.45	21.53	0.1510	0.0680	0.0120
PG08205	21.53	22.50	0.1990	0.1000	0.0150
PG08206	22.50	23.55	0.1820	0.0600	0.0150
PG08207	23.55	24.53	0.1570	0.0550	0.0160
PG08208	24.53	25.59	0.1240	0.0360	0.0150
PG08209	25.59	26.40	0.1610	0.0370	0.0180
PG08210	26.40	27.40	0.1680	0.0830	0.0140
PG08211	27.40	28.55	0.1370	0.0620	0.0130
PG08212	28.55	29.36	0.1240	0.0660	0.0110
PG08213	29.36	30.28	0.1510	0.0760	0.0130
PG08214	30.28	31.28	0.0510	0.0330	0.0060
PG08215	31.28	32.33	0.0470	0.0400	0.0070
PG08216	32.33	33.23	0.0840	0.0300	0.0100
PG08217	33.23	34.23	0.1970	0.0730	0.0160
PG08218	34.23	35.23	0.1330	0.0790	0.0110
PG08219	35.23	36.23	0.0820	0.0610	0.0090
PG08221	36.23	37.23	0.1150	0.0570	0.0110
PG08222	37.23	38.23	0.0710	0.0340	0.0080
PG08223	38.23	39.70	0.0950	0.0430	0.0090
PG08224	39.70	40.70	0.0200	0.0140	0.0040
PG08225	40.70	41.70	0.0940	0.0430	0.0070
PG08226	41.70	42.70	0.0740	0.0400	0.0060
PG08227	42.70	43.70	0.1090	0.0580	0.0090
PG08228	43.70	44.70	0.0720	0.0380	0.0060
PG08229	44.70	45.70	0.0500	0.0330	0.0050
PG08230	45.70	46.70	0.0240	0.0190	0.0040
PG08231	46.70	47.70	0.0520	0.0430	0.0060
PG08232	47.70	48.70	0.0470	0.0270	0.0050
PG08233	48.70	49.70	0.0250	0.0160	0.0040
PG08234	49.70	50.50	0.1000	0.1020	0.0070
PG08235	50.50	51.50	0.1880	0.1170	0.0120
PG08236	51.50	52.50	0.1680	0.0750	0.0110
PG08237	52.50	53.50	0.2110	0.0800	0.0140
PG08238	53.50	54.16	0.0930	0.0580	0.0070

Hole Number: ES07-105

Units: METRIC

Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
PG08239	54.16	55.16	0.1460	0.0690	0.0100
PG08241	55.16	56.16	0.2630	0.0930	0.0180
PG08242	56.16	57.00	0.1850	0.1120	0.0130
PG08243	57.00	58.00	0.2020	0.0670	0.0140
PG08244	58.00	59.00	0.0900	0.0480	0.0070
PG08245	59.00	60.05	0.1140	0.0940	0.0080
PG08246	60.05	61.05	0.1530	0.0650	0.0100
PG08247	61.05	62.05	0.3840	0.1010	0.0260
PG08248	62.05	63.05	0.1070	0.0810	0.0080
PG08249	63.05	64.00	0.0270	0.0180	0.0030
PG08250	64.00	65.00	0.1090	0.0680	0.0070
PG08301	65.00	66.00	0.2240	0.0850	0.0140
PG08302	66.00	67.00	0.2860	0.1150	0.0190
PG08303	67.00	68.00	0.2040	0.0680	0.0150
PG08304	68.00	69.00	0.1400	0.0750	0.0100
PG08305	69.00	70.00	0.2080	0.0760	0.0150
PG08306	70.00	71.00	0.2230	0.0740	0.0160
PG08307	71.00	72.00	0.2400	0.0750	0.0190
PG08308	72.00	73.00	0.2310	0.1380	0.0150
PG08309	73.00	74.00	0.2310	0.1650	0.0150
PG08310	74.00	75.00	0.2010	0.0670	0.0130
PG08311	75.00	76.00	0.1300	0.0730	0.0090
PG08312	76.00	77.00	0.0540	0.0780	0.0040
PG08313	77.00	78.00	0.1600	0.0690	0.0100
PG08314	78.00	78.30	0.4920	0.3900	0.0300
PG08315	78.30	79.00	0.2230	0.0970	0.0130
PG08316	79.00	80.00	0.2030	0.0880	0.0120
PG08317	80.00	81.00	0.2380	0.1570	0.0150
PG08318	81.00	82.00	0.1320	0.0620	0.0110
PG08319	82.00	83.00	0.2280	0.1390	0.0140
PG08321	83.00	84.00	0.2580	0.1010	0.0160
PG08322	84.00	85.00	0.2790	0.1490	0.0180
PG08323	85.00	86.00	0.1830	0.0580	0.0130
PG08324	86.00	87.00	0.1340	0.0710	0.0090
PG08325	87.00	88.00	0.1690	0.0720	0.0100
PG08326	88.00	89.00	0.0480	0.0350	0.0040
PG08327	89.00	90.00	0.0470	0.0370	0.0040

Hole Number: ES07-105

Units: METRIC

Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
PG08328	90.00	91.00	0.1240	0.1260	0.0080
PG08329	91.00	92.00	0.2940	0.1720	0.0170
PG08330	92.00	93.00	0.2540	0.1150	0.0150
PG08331	93.00	94.00	0.2590	0.1730	0.0160
PG08332	94.00	95.00	0.2340	0.1630	0.0150
PG08333	95.00	96.00	0.1730	0.1230	0.0120
PG08334	96.00	97.00	0.1150	0.1160	0.0080
PG08335	97.00	98.00	0.3530	0.2040	0.0220
PG08336	98.00	99.00	0.2020	0.1050	0.0140
PG08337	99.00	100.00	0.1620	0.0650	0.0120
PG08338	100.00	101.00	0.1420	0.0860	0.0100
PG08339	101.00	102.00	0.1670	0.0870	0.0110
PG08341	102.00	103.00	0.2120	0.0800	0.0170
PG08342	103.00	104.00	0.1290	0.0410	0.0140
PG08343	104.00	105.00	0.1570	0.0510	0.0160
PG08344	105.00	106.00	0.1380	0.0470	0.0150
PG08345	106.00	107.00	0.1230	0.0480	0.0130
PG08346	107.00	108.00	0.2490	0.0870	0.0170
PG08347	108.00	109.00	0.1650	0.1040	0.0120
PG08348	109.00	110.00	0.2060	0.1120	0.0140
PG08349	110.00	111.00	0.1220	0.0640	0.0100
PG08350	111.00	112.00	0.1010	0.0550	0.0080
PG08351	112.00	113.00	0.0950	0.0510	0.0080
PG08352	113.00	114.00	0.2260	0.1020	0.0150
PG08353	114.00	115.00	0.2470	0.1140	0.0160
PG08354	115.00	116.00	0.2120	0.1470	0.0140
PG08355	116.00	117.00	0.1450	0.0740	0.0110
PG08356	117.00	118.00	0.1290	0.0760	0.0090
PG08357	118.00	119.00	0.0660	0.0660	0.0080
PG08358	119.00	120.00	0.0860	0.0630	0.0070
PG08359	120.00	121.00	0.1790	0.1150	0.0130
PG08361	121.00	122.00	0.1800	0.0690	0.0140
PG08362	122.00	123.00	0.1240	0.0570	0.0110
PG08363	123.00	124.00	0.1370	0.1880	0.0110
PG08364	124.00	125.00	0.1690	0.1030	0.0120
PG08365	125.00	126.00	0.1230	0.0560	0.0080
PG08366	126.00	127.00	0.0940	0.0640	0.0090

Hole Number: ES07-105

Units: METRIC

Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
PG08367	127.00	128.00	0.1550	0.0510	0.0180
PG08368	128.00	129.00	0.1830	0.0760	0.0200
PG08369	129.00	130.00	0.1450	0.0490	0.0150
PG08370	130.00	131.00	0.1620	0.0560	0.0180
PG08371	131.00	132.00	0.1640	0.0820	0.0180
PG08372	132.00	133.00	0.1500	0.0520	0.0180
PG08373	133.00	134.00	0.1450	0.0440	0.0180
PG08374	134.00	135.00	0.1420	0.0610	0.0180
PG08375	135.00	136.00	0.0520	0.0220	0.0080
PG08376	136.00	137.00	0.0040	0.0025	0.0030
PG08377	137.00	138.00	0.0040	0.0025	0.0030
PG08378	138.00	139.00	0.0030	0.0025	0.0020
PG08379	139.00	140.00	0.0140	0.0110	0.0030
PG08381	140.00	141.00	0.0990	0.0430	0.0070
PG08382	141.00	142.00	0.0960	0.0510	0.0070
PG08383	142.00	143.00	0.1270	0.0810	0.0080
PG08384	143.00	144.00	0.1470	0.0810	0.0090
PG08385	144.00	145.00	0.1170	0.0560	0.0080
PG08386	145.00	146.00	0.0760	0.0350	0.0060
PG08387	146.00	147.00	0.0780	0.0480	0.0060
PG08388	147.00	148.00	0.0670	0.0340	0.0060
PG08389	148.00	149.00	0.0270	0.0150	0.0040
PG08390	149.00	150.00	0.0920	0.0470	0.0080
PG08391	150.00	151.00	0.0630	0.0360	0.0060
PG08392	151.00	152.00	0.0660	0.0310	0.0060
PG08393	152.00	153.00	0.0980	0.0490	0.0070
PG08394	153.00	154.00	0.0870	0.0500	0.0070
PG08395	154.00	155.00	0.2140	0.3270	0.0150
PG08396	155.00	155.33	4.1120	0.0990	0.2520
PG08397	155.33	155.66	3.9670	0.0840	0.2380
PG08398	155.66	156.03	3.2530	0.5620	0.1930
PG08399	156.03	157.00	0.1900	0.2430	0.0130
PG08401	157.00	158.00	0.0190	0.0120	0.0030
PG08402	163.35	164.35	0.0870	0.0260	0.0130
PG08403	164.35	165.37	0.0680	0.0110	0.0120
PG08404	165.37	166.06	0.0740	0.0180	0.0110
PG08405	166.06	166.75	0.0770	0.0490	0.0110

Hole Number: ES07-105

Units: METRIC

Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
PG08406	166.75	167.06	0.7310	0.1410	0.0580
PG08407	167.06	168.04	0.0940	0.0180	0.0130
PG08408	168.04	169.08	0.0860	0.0320	0.0110
PG08409	169.08	170.05	0.1450	0.0660	0.0130
PG08410	170.05	171.07	0.1450	0.0440	0.0140
PG08411	171.07	172.08	0.1140	0.0290	0.0110
PG08412	172.08	173.10	0.0850	0.0090	0.0100
PG08413	173.10	174.00	0.0930	0.0060	0.0120
PG08414	174.00	174.40	0.3030	0.0730	0.0370
PG08415	174.40	175.40	0.0120	0.0060	0.0040
PG08416	184.37	185.37	0.0050	0.0025	0.0030
PG08417	185.37	185.67	0.4220	0.4660	0.0770
PG08418	185.67	186.67	0.0190	0.0180	0.0060
PG08419	193.35	194.35	0.0230	0.0210	0.0050
PG08421	194.35	194.65	0.1430	0.0610	0.0190
PG08422	194.65	195.65	0.0260	0.0120	0.0060