

Hole Number: ES08-162

Units: METRIC

Project Name: Norway - Espedalen	Primary Coordinates Grid: UTM84-32N	Destination Coordinates Grid: UTM:	Collar Dip: -78.90
Project Number: 201	North: 6805211.00	North: 61.38	Collar Az: 232.70
Location: Surface	East: 533867.00	East: 9.63	Length: 197.31 (m)
	Elev: 747.00	Elev: 747.00	Start Depth: 0.00 (m)
Date Started: Jun 16, 2008	Collar Survey: N	Plugged: N	Contractor: Arctic Drilling A/S
Date Completed: Jun 19, 2008	Multishot Survey: N	Hole Size: BQ	Core Storage: Tyrstrand
Logged By: cmnor	Pulse EM Survey: N	Casing: Left in Hole	Final Depth: 197.31 (m)

Comments: 50m northwest along strike of ES08-141.

Mineralization (very significant, intersections up to 10cm of massive sulphides - Po and Cpy)

21.70 - 23.95	2-5% Po, trace Cpy
41.35 - 43.00	1 - 3% Po, trace Cpy
43.00 - 43.50	5-10% Po, 2% Cpy
43.50 - 59.10	3-5% Po, <1% Cpy
59.10 - 59.60	7-10% Po, 1-2% Cpy
59.60 - 69.00	2-4% Po, trace-1% Cpy
69.00 - 71.00	5-7% Po, 1-2% Cpy
73.00 - 102.50	3-5% Po, trace-2% Cpy
102.5 - 104.50	5-7% Po, 2% Cpy
104.00 - 109.50	4% Po, trace Cpy
109.50 - 110.00	10-15% Po, 2% Cpy
110.00 - 113.00	4% Po, trace Cpy
113.00 - 116.00	3-4% Po, trace Cpy
116.00 - 116.72	5-7% Po, trace Cpy
116.72 - 117.22	20% Po, ~2% Cpy
117.22 - 125.00	trace - 1% Po
130.95 - 131.25	2-3% Po, trace Cpy
132.10 - 132.40	60-65% Po + Cpy

Sample Averages

Hole Number: ES08-162

Units: METRIC

Detailed Lithology		Assay Data							
From (m)	To (m)	Lithology	Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
0	10.40	O/B, Overburden							
10.40	41.35	ANOR, Anorthosite ANORTHOSITE -typical anorthosite, light grey to white in color, fine to medium grained -minor fractures and faults throughout -LC @ 80 degrees to CA  Unit not Mineralized MINOR INTERVALS: Minor Interval: 14.75 - 18.15 MD, Mafic Dike MAFIC DYKE -green, very fine grained -UC faulted @ 40 degrees to CA -minor qtz-carb stringers throughout -LC faulted @ 45 degrees to CA  Unit not Mineralized Structure 14.75 - 14.75 : UC Upper Contact, 40 Deg to CA faulted 17.50 - 17.50 : FLT Fault, 60 Deg to CA 18.15 - 18.15 : LC Lower Contact, 45 Deg to CA faulted Minor Interval: 21.7 - 23.98 PYXT, Pyroxenite PYROXENITE -grey to dark grey in color, medium grained -UC @ 30 degrees to CA - 1-3mm fine grained opx? -LC @ 40 degrees to CA  Mineralization 21.70 - 23.95 2-5% Po, trace Cpy  Mineralization 22.95 - 23.98 : PO Pyrrhotite, DIS Disseminated, 4.5% 4-5% Po, trace Cpy 22.35 - 22.95 : PO Pyrrhotite, Net Net Textured, 3% 2-4% Po, trace Cpy 21.70 - 22.35 : PO Pyrrhotite, Net Net Textured, 2% Structure 21.70 - 21.70 : UC Upper Contact, 30 Deg to CA 23.98 - 23.98 : LC Lower Contact, 40 Deg to CA	BL00694	20.20	21.20	1.00	0.0020	0.0025	0.0005
			BL00695	21.20	21.70	0.50	0.0020	0.0025	0.0005
			BL00696	21.70	22.35	0.65	0.1690	0.0730	0.0140
			BL00697	22.35	22.95	0.60	0.2420	0.1050	0.0220
			BL00698	22.95	23.28	0.33	0.2520	0.1020	0.0200
			BL00699	23.28	23.68	0.40	0.2610	0.1470	0.0210
			BL00701	23.68	23.98	0.30	0.2610	0.1340	0.0210
			BL00702	23.98	24.50	0.52	0.0060	0.0050	0.0005
			BL00703	24.50	25.50	1.00	0.0020	0.0025	0.0005
			BL00704	39.90	40.90	1.00	0.0030	0.0025	0.0010
			BL00705	40.90	41.35	0.45	0.0040	0.0025	0.0010

## DETAILED LOG

Hole Number: ES08-162

Units: METRIC

Detailed Lithology		Assay Data							
From (m)	To (m)	Lithology	Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
41.35	125.00	PYXT, Pyroxenite	BL00706	41.35	42.00	0.65	0.0410	0.0250	0.0040
		PYROXENITE	BL00707	42.00	43.00	1.00	0.2050	0.1010	0.0170
		-dark grey to black, fine grained and massive	BL00708	43.00	43.50	0.50	0.4640	0.1710	0.0380
		-UC @ 80 degrees to CA	BL00709	43.50	44.00	0.50	0.5230	0.1350	0.0430
		- 2-5mm fine grained opx grains throughout unit	BL00710	44.00	44.50	0.50	0.2620	0.2050	0.0210
		-talcose bands local to fractures and faulting	BL00711	44.50	45.00	0.50	0.1920	0.1500	0.0160
		-strongly magnetic	BL00712	45.00	46.00	1.00	0.1510	0.0770	0.0140
		-fractures and faulting throughout unit (broken core is frequent)	BL00713	46.00	47.00	1.00	0.1490	0.0510	0.0150
		-LC faulted @	BL00714	47.00	48.00	1.00	0.2210	0.0790	0.0220
		Mineralization is as follows	BL00715	48.00	49.00	1.00	0.2110	0.0700	0.0200
		41.35 - 43.00 1 - 3% Po, trace Cpy	BL00716	49.00	50.00	1.00	0.2720	0.1210	0.0250
		43.00 - 43.50 5-10% Po, 2% Cpy	BL00717	50.00	51.00	1.00	0.2740	0.0770	0.0270
		43.50 - 59.10 3-5% Po, <1% Cpy	BL00718	51.00	52.00	1.00	0.2300	0.0970	0.0210
		59.10 - 59.60 7-10% Po, 1-2% Cpy	BL00719	52.00	53.00	1.00	0.3430	0.1230	0.0300
		59.60 - 69.00 2-4% Po, trace-1% Cpy	BL00721	53.00	54.00	1.00	0.2250	0.1220	0.0210
		69.00 - 71.00 5-7% Po, 1-2% Cpy	BL00722	54.00	55.00	1.00	0.1410	0.0590	0.0160
		73.00 - 102.50 3-5% Po, trace-2% Cpy	BL00723	55.00	56.00	1.00	0.1500	0.0530	0.0160
		102.5 - 104.50 5-7% Po, 2% Cpy	BL00724	56.00	57.00	1.00	0.1710	0.0870	0.0180
		104.00 - 109.50 4% Po, trace Cpy	BL00725	57.00	58.00	1.00	0.2530	0.1000	0.0240
		109.50 - 110.00 10-15% Po, 2%Cpy	BL00726	58.00	59.10	1.10	0.3210	0.1480	0.0290
		110.00 - 113.00 4% Po, trace Cpy	BL00727	59.10	59.60	0.50	0.3540	0.1480	0.0320
		113.00 - 116.00 3-4% Po, trace Cpy	BL00728	59.60	60.00	0.40	0.1440	0.0810	0.0170
		116.00 - 116.72 5-7% Po, trace Cpy	BL00729	60.00	61.00	1.00	0.2250	0.0850	0.0230
		116.72 - 117.22 20% Po, ~2% Cpy	BL00730	61.00	62.00	1.00	0.2500	0.0920	0.0240
		117.22 - 125.00 trace - 1% Po	BL00731	62.00	63.00	1.00	0.2940	0.1610	0.0270
		Mineralization	BL00732	63.00	64.00	1.00	0.3290	0.1130	0.0300
		117.22 - 125.00 : PO Pyrrhotite, DIS Disseminated, 1%	BL00733	64.00	65.00	1.00	0.2980	0.1330	0.0280
		116.72 - 117.22 : PO Pyrrhotite, BL Blebby, 20%	BL00734	65.00	66.00	1.00	0.2300	0.1110	0.0200
		~20% Po, ~2%Cpy	BL00735	66.00	67.00	1.00	0.2510	0.0990	0.0230
		116.00 - 116.72 : PO Pyrrhotite, Net Net Textured, 6%	BL00736	67.00	68.00	1.00	0.2790	0.1650	0.0250
		5-7%	BL00737	68.00	69.00	1.00	0.3620	0.0850	0.0320
		113.00 - 116.00 : PO Pyrrhotite, Net Net Textured, 3%	BL00738	69.00	70.00	1.00	0.3420	0.1200	0.0310
		3-4%	BL00739	70.00	71.00	1.00	0.3340	0.1640	0.0290
		110.00 - 113.00 : PO Pyrrhotite, BL Blebby, 4%	BL00741	71.00	72.00	1.00	0.3490	0.0950	0.0280
		3-5%	BL00742	72.00	73.00	1.00	0.2840	0.1260	0.0250
		109.50 - 110.00 : PO Pyrrhotite, BL Blebby, 12%	BL00743	73.00	74.00	1.00	0.2560	0.0900	0.0220
		10-15%	BL00744	74.00	75.00	1.00	0.2390	0.1700	0.0200
		104.00 - 109.50 : PO Pyrrhotite, Net Net Textured, 4%	BL00745	75.00	75.50	0.50	0.2660	0.0860	0.0230
		102.00 - 104.00 : PO Pyrrhotite, BL Blebby, 6%	BL00746	75.50	76.00	0.50	0.1860	0.0690	0.0160
		5-7% Po, 2% Cpy	BL00747	76.00	77.00	1.00	0.3270	0.1070	0.0290
		102.00 - 102.50 : PO Pyrrhotite, Net Net Textured, 4%	BL00748	77.00	77.60	0.60	0.3140	0.1360	0.0280
		3-5% Po, trace Cpy	BL00749	77.60	78.90	1.30	0.1820	0.0770	0.0190
		101.00 - 102.00 : PO Pyrrhotite, DIS Disseminated, 2%	BL00750	78.90	79.98	1.08	0.0060	0.0120	0.0030
		1-3% Po, trace Cpy							

## DETAILED LOG

Hole Number: ES08-162

Units: METRIC

Detailed Lithology		Assay Data							
From (m)	To (m)	Lithology	Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
		Mineralization	BL00751	79.98	81.00	1.02	0.0050	0.0110	0.0030
		98.00 - 101.00 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, 1% Cpy	BL00752	81.00	82.00	1.00	0.2420	0.0880	0.0220
		96.00 - 98.00 : PO Pyrrhotite, Net Net Textured, 1%	BL00753	82.00	83.00	1.00	0.1840	0.0670	0.0190
		95.00 - 96.00 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, trace Cpy	BL00754	83.00	84.00	1.00	0.1840	0.0430	0.0190
		94.00 - 95.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3% Po	BL00755	84.00	85.00	1.00	0.1970	0.0400	0.0200
		93.00 - 94.00 : PO Pyrrhotite, DIS Disseminated, 1%	BL00756	85.00	86.00	1.00	0.3260	0.1310	0.0280
		91.00 - 93.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3% Po, trace Cpy	BL00757	86.00	87.00	1.00	0.1990	0.1240	0.0180
		90.00 - 91.00 : PO Pyrrhotite, Net Net Textured, 1%	BL00758	87.00	88.00	1.00	0.2120	0.1120	0.0190
		89.00 - 89.40 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, trace Cpy	BL00759	88.00	89.00	1.00	0.1690	0.1190	0.0160
		88.00 - 89.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3%	BL00761	89.00	89.40	0.40	0.2700	0.0760	0.0220
		82.00 - 88.00 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, trace Cpy	BL00762	89.40	90.00	0.60	0.0260	0.0120	0.0050
		81.00 - 82.00 : PO Pyrrhotite, Net Net Textured, 1%	BL00763	90.00	91.00	1.00	0.1650	0.1600	0.0150
		79.98 - 81.00 : PO Pyrrhotite, Net Net Textured, 4% 4-5% Po, trace Cpy	BL00764	91.00	92.00	1.00	0.1740	0.2840	0.0170
		77.00 - 77.60 : PO Pyrrhotite, Net Net Textured, 5% trace Cpy	BL00765	92.00	93.00	1.00	0.0690	0.0360	0.0090
		76.00 - 77.00 : PO Pyrrhotite, BL Blebby, 6% 5-7% Po, 1-2% Cpy	BL00766	93.00	94.00	1.00	0.0760	0.0350	0.0110
		75.50 - 76.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3% Po, trace Cpy	BL00767	94.00	95.00	1.00	0.0770	0.0370	0.0110
		75.00 - 75.50 : PO Pyrrhotite, Net Net Textured, 5% trace Cpy	BL00768	95.00	96.00	1.00	0.1090	0.0370	0.0120
		73.00 - 75.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3% Po	BL00769	96.00	97.00	1.00	0.0950	0.0370	0.0110
		69.00 - 71.00 : PO Pyrrhotite, BL Blebby, 6% 5-7% Po, 2% Cpy	BL00770	97.00	98.00	1.00	0.1190	0.0900	0.0140
		67.00 - 69.00 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, 1% Cpy	BL00771	98.00	99.00	1.00	0.1340	0.0360	0.0140
		65.00 - 67.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3% Po	BL00772	99.00	100.00	1.00	0.1230	0.0310	0.0130
		60.00 - 65.00 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, 1% Cpy	BL00773	100.00	101.00	1.00	0.0980	0.0710	0.0110
		59.60 - 60.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3% Po, trace Cpy	BL00774	101.00	102.00	1.00	0.1600	0.0810	0.0160
		59.10 - 59.60 : PO Pyrrhotite, BL Blebby, 7.5% 7-10% Po, 1-2% Cpy	BL00775	102.00	102.50	0.50	0.1990	0.0490	0.0190
		58.00 - 59.10 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, 1% Cpy	BL00776	102.50	103.00	0.50	0.2650	0.0990	0.0250
			BL00777	103.00	104.00	1.00	0.2940	0.1330	0.0280
			BL00778	104.00	105.00	1.00	0.1300	0.1170	0.0130
			BL00779	105.00	106.00	1.00	0.1560	0.1020	0.0160
			BL00781	106.00	107.00	1.00	0.1330	0.0940	0.0130
			BL00782	107.00	108.00	1.00	0.2030	0.0720	0.0190
			BL00783	108.00	109.00	1.00	0.1660	0.0730	0.0140
			BL00784	109.00	109.50	0.50	0.1210	0.0700	0.0100
			BL00785	109.50	110.00	0.50	0.2310	0.0980	0.0190
			BL00786	110.00	111.00	1.00	0.1930	0.1100	0.0160
			BL00787	111.00	112.00	1.00	0.1790	0.0760	0.0150
			BL00788	112.00	113.00	1.00	0.1780	0.0520	0.0150
			BL00789	113.00	114.00	1.00	0.1290	0.0560	0.0130
			BL00790	114.00	115.00	1.00	0.0990	0.0500	0.0100
			BL00791	115.00	115.50	0.50	0.1290	0.0490	0.0120
			BL00792	115.50	116.00	0.50	0.1990	0.0370	0.0170
			BL00793	116.00	116.72	0.72	0.2740	0.0390	0.0230
			BL00794	116.72	117.22	0.50	0.3600	0.0090	0.0300
			BL00795	117.22	118.00	0.78	0.0200	0.0310	0.0040

## DETAILED LOG

Hole Number: ES08-162

Units: METRIC

Detailed Lithology		Assay Data							
From (m)	To (m)	Lithology	Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
		Mineralization	BL00796	118.00	119.00	1.00	0.1300	0.0420	0.0120
		46.00 - 58.00 : PO Pyrrhotite, Net Net Textured, 2% 1-3% Po, trace Cpy	BL00797	119.00	120.00	1.00	0.0580	0.0230	0.0070
		46.00 - 54.00 : PO Pyrrhotite, Net Net Textured, 4% 3-5% Po, ~1% Cpy	BL00798	120.00	121.00	1.00	0.0490	0.0130	0.0070
		46.00 - 51.00 : PO Pyrrhotite, Net Net Textured, 3%	BL00799	121.00	122.00	1.00	0.0320	0.0080	0.0060
		46.00 - 47.00 : PO Pyrrhotite, DIS Disseminated, 1%	BL00801	122.00	123.00	1.00	0.0360	0.0080	0.0060
		45.00 - 46.00 : PO Pyrrhotite, Net Net Textured, 2.5% 2-3% Po, trace Cpy	BL00802	123.00	124.00	1.00	0.0360	0.0060	0.0060
		44.00 - 45.00 : PO Pyrrhotite, BL Blebby, 1%	BL00803	124.00	125.00	1.00	0.0600	0.0180	0.0080
		43.50 - 44.00 : PO Pyrrhotite, BL Blebby, 5%							
		43.00 - 43.50 : PO Pyrrhotite, BL Blebby, 7%							
		5-10% Po, 2% Cpy							
		42.00 - 43.00 : PO Pyrrhotite, DIS Disseminated, 2% 1-3% Po, trace Cpy							
		41.35 - 42.00 : PO Pyrrhotite, DIS Disseminated, 1%							
		Structure							
		114.00 - 114.00 : FLT Fault, 40 Deg to CA							
		119.30 - 119.30 : FLT Fault, 15 Deg to CA							
125.00	130.95	MD, Mafic Dike	BL00804	125.00	126.00	1.00	0.0450	0.0140	0.0060
		MAFIC DYKE	BL00805	126.00	127.00	1.00	0.0010	0.0050	0.0020
		-green in color, very fine grained	BL00806	127.00	128.00	1.00	0.0010	0.0060	0.0030
		-foliated @ 70 degrees to CA	BL00807	128.00	129.00	1.00	0.0010	0.0070	0.0020
		-minor chloritic stringers/bands throughout	BL00808	129.00	130.00	1.00	0.0005	0.0070	0.0030
		-minor fractures throughout							
		Unit not Mineralized							

Hole Number: ES08-162

Units: METRIC

Detailed Lithology		Lithology	Assay Data						
From (m)	To (m)		Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
130.95	155.42	ANOR, Anorthosite	BL00809	130.95	131.25	0.30	0.0200	0.0230	0.0040
		ANORTHOSITE	BL00811	131.25	132.10	0.85	0.0570	0.0290	0.0020
		-light grey to grey and fine to medium grained	BL00812	132.10	132.40	0.30	0.5880	0.1860	0.0430
		-mafic dykes/intersections throughout unit	BL00813	132.40	132.90	0.50	0.0040	0.0100	0.0030
		-sericitic alteration - minor stringers throughout	BL00814	132.90	133.90	1.00	0.0070	0.0160	0.0030
		-several minor units of mafic dyke (and banding of mafic component due to intersections of md)							
		-minor fractures throughout							
		-LC @ 80 degrees to CA							
		Mineralization							
		130.95 - 131.25 2-3% Po, trace Cpy							
		132.10 - 132.40 60-65% Po + Cpy							
		Mineralization							
		132.10 - 132.40 : PO Pyrrhotite, SM Semi-Massive, 60%							
		60-65% Po + Cpy							
		130.95 - 131.25 : PO Pyrrhotite, Net Net Textured, 2.5%							
		2-3% Po, trace Cpy							
		MINOR INTERVALS:							
		Minor Interval:							
		132.4 - 133.8 MD, Mafic Dike							
		MAFIC DYKE							
		-green in color, fine grained							
		-foliated at 70 degrees to CA							
		-minor fractures throughout							
		Unit not Mineralized							
		Minor Interval:							
		136.1 - 140.95 MD, Mafic Dike							
		MAFIC DYKE							
		-green in color, fine to medium grained							
		-foliated from 70-85 degrees to CA							
		-minor fractures throughout							
		Unit not Mineralized							
		Minor Interval:							
		142.72 - 146.72 MD, Mafic Dike							
		MAFIC DYKE							
		-green in color, fine to medium grained, UC @ 50 degrees to CA							
		-foliated at 70 degrees to CA							
		-minor fractures throughout							
		Unit not Mineralized							

Hole Number: ES08-162

Units: METRIC

Detailed Lithology		Lithology	Assay Data						
From (m)	To (m)		Sample Number	From (m)	To (m)	Length (m)	Ni%	Cu%	Co%
155.42	166.20	MD, Mafic Dike MAFIC DYKE -green in color, fine grained -minor chloritic stringers/banding @ 80 degrees to CA -minor 30cm intersection of Anorthosite @ 163.45 -minor fractures throughout							
166.20	197.30	ANOR, Anorthosite ANORTHOSITE -light grey to grey and fine to medium grained -mafic dykes/intersections throughout unit -sericitic alteration - minor stringers throughout -minor fractures throughout  Trace, blebby Po @ 175.5 Mineralization 175.35 - 179.05 : Cpy Chalcopyrite, DIS Disseminated, 1% 175.35 - 179.05 : PO Pyrrhotite, DIS Disseminated, 3%	BL00848	173.35	174.35	1.00	0.0050	0.0025	0.0020
			BL00849	174.35	175.35	1.00	0.0050	0.0025	0.0020
			BL00850	175.35	176.35	1.00	0.0120	0.0060	0.0040
			BL00851	176.35	177.20	0.85	0.0160	0.0120	0.0030
			BL00852	177.20	178.10	0.90	0.0380	0.0330	0.0050
			BL00853	178.10	179.10	1.00	0.0100	0.0025	0.0030
			BL00854	179.10	180.10	1.00	0.0040	0.0025	0.0020
			BL00855	180.10	181.10	1.00	0.0040	0.0025	0.0020
197.30	197.31	EOH, End of Hole							

## Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
BL00694	20.20	21.20	0.0020	0.0025	0.0005
BL00695	21.20	21.70	0.0020	0.0025	0.0005
BL00696	21.70	22.35	0.1690	0.0730	0.0140
BL00697	22.35	22.95	0.2420	0.1050	0.0220
BL00698	22.95	23.28	0.2520	0.1020	0.0200
BL00699	23.28	23.68	0.2610	0.1470	0.0210
BL00701	23.68	23.98	0.2610	0.1340	0.0210
BL00702	23.98	24.50	0.0060	0.0050	0.0005
BL00703	24.50	25.50	0.0020	0.0025	0.0005
BL00704	39.90	40.90	0.0030	0.0025	0.0010
BL00705	40.90	41.35	0.0040	0.0025	0.0010
BL00706	41.35	42.00	0.0410	0.0250	0.0040
BL00707	42.00	43.00	0.2050	0.1010	0.0170
BL00708	43.00	43.50	0.4640	0.1710	0.0380
BL00709	43.50	44.00	0.5230	0.1350	0.0430
BL00710	44.00	44.50	0.2620	0.2050	0.0210
BL00711	44.50	45.00	0.1920	0.1500	0.0160
BL00712	45.00	46.00	0.1510	0.0770	0.0140
BL00713	46.00	47.00	0.1490	0.0510	0.0150

Hole Number: ES08-162

Units: METRIC

## Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
BL00714	47.00	48.00	0.2210	0.0790	0.0220
BL00715	48.00	49.00	0.2110	0.0700	0.0200
BL00716	49.00	50.00	0.2720	0.1210	0.0250
BL00717	50.00	51.00	0.2740	0.0770	0.0270
BL00718	51.00	52.00	0.2300	0.0970	0.0210
BL00719	52.00	53.00	0.3430	0.1230	0.0300
BL00721	53.00	54.00	0.2250	0.1220	0.0210
BL00722	54.00	55.00	0.1410	0.0590	0.0160
BL00723	55.00	56.00	0.1500	0.0530	0.0160
BL00724	56.00	57.00	0.1710	0.0870	0.0180
BL00725	57.00	58.00	0.2530	0.1000	0.0240
BL00726	58.00	59.10	0.3210	0.1480	0.0290
BL00727	59.10	59.60	0.3540	0.1480	0.0320
BL00728	59.60	60.00	0.1440	0.0810	0.0170
BL00729	60.00	61.00	0.2250	0.0850	0.0230
BL00730	61.00	62.00	0.2500	0.0920	0.0240
BL00731	62.00	63.00	0.2940	0.1610	0.0270
BL00732	63.00	64.00	0.3290	0.1130	0.0300
BL00733	64.00	65.00	0.2980	0.1330	0.0280
BL00734	65.00	66.00	0.2300	0.1110	0.0200
BL00735	66.00	67.00	0.2510	0.0990	0.0230
BL00736	67.00	68.00	0.2790	0.1650	0.0250
BL00737	68.00	69.00	0.3620	0.0850	0.0320
BL00738	69.00	70.00	0.3420	0.1200	0.0310
BL00739	70.00	71.00	0.3340	0.1640	0.0290
BL00741	71.00	72.00	0.3490	0.0950	0.0280
BL00742	72.00	73.00	0.2840	0.1260	0.0250
BL00743	73.00	74.00	0.2560	0.0900	0.0220
BL00744	74.00	75.00	0.2390	0.1700	0.0200
BL00745	75.00	75.50	0.2660	0.0860	0.0230
BL00746	75.50	76.00	0.1860	0.0690	0.0160
BL00747	76.00	77.00	0.3270	0.1070	0.0290
BL00748	77.00	77.60	0.3140	0.1360	0.0280
BL00749	77.60	78.90	0.1820	0.0770	0.0190
BL00750	78.90	79.98	0.0060	0.0120	0.0030
BL00751	79.98	81.00	0.0050	0.0110	0.0030
BL00752	81.00	82.00	0.2420	0.0880	0.0220



Hole Number: ES08-162

Units: METRIC

## Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
BL00753	82.00	83.00	0.1840	0.0670	0.0190
BL00754	83.00	84.00	0.1840	0.0430	0.0190
BL00755	84.00	85.00	0.1970	0.0400	0.0200
BL00756	85.00	86.00	0.3260	0.1310	0.0280
BL00757	86.00	87.00	0.1990	0.1240	0.0180
BL00758	87.00	88.00	0.2120	0.1120	0.0190
BL00759	88.00	89.00	0.1690	0.1190	0.0160
BL00761	89.00	89.40	0.2700	0.0760	0.0220
BL00762	89.40	90.00	0.0260	0.0120	0.0050
BL00763	90.00	91.00	0.1650	0.1600	0.0150
BL00764	91.00	92.00	0.1740	0.2840	0.0170
BL00765	92.00	93.00	0.0690	0.0360	0.0090
BL00766	93.00	94.00	0.0760	0.0350	0.0110
BL00767	94.00	95.00	0.0770	0.0370	0.0110
BL00768	95.00	96.00	0.1090	0.0370	0.0120
BL00769	96.00	97.00	0.0950	0.0370	0.0110
BL00770	97.00	98.00	0.1190	0.0900	0.0140
BL00771	98.00	99.00	0.1340	0.0360	0.0140
BL00772	99.00	100.00	0.1230	0.0310	0.0130
BL00773	100.00	101.00	0.0980	0.0710	0.0110
BL00774	101.00	102.00	0.1600	0.0810	0.0160
BL00775	102.00	102.50	0.1990	0.0490	0.0190
BL00776	102.50	103.00	0.2650	0.0990	0.0250
BL00777	103.00	104.00	0.2940	0.1330	0.0280
BL00778	104.00	105.00	0.1300	0.1170	0.0130
BL00779	105.00	106.00	0.1560	0.1020	0.0160
BL00781	106.00	107.00	0.1330	0.0940	0.0130
BL00782	107.00	108.00	0.2030	0.0720	0.0190
BL00783	108.00	109.00	0.1660	0.0730	0.0140
BL00784	109.00	109.50	0.1210	0.0700	0.0100
BL00785	109.50	110.00	0.2310	0.0980	0.0190
BL00786	110.00	111.00	0.1930	0.1100	0.0160
BL00787	111.00	112.00	0.1790	0.0760	0.0150
BL00788	112.00	113.00	0.1780	0.0520	0.0150
BL00789	113.00	114.00	0.1290	0.0560	0.0130
BL00790	114.00	115.00	0.0990	0.0500	0.0100
BL00791	115.00	115.50	0.1290	0.0490	0.0120

Hole Number: ES08-162

Units: METRIC

## Samples

Sample Number	From (m)	To (m)	Ni%	Cu%	Co%
Sample Type	ASSAY				
BL00792	115.50	116.00	0.1990	0.0370	0.0170
BL00793	116.00	116.72	0.2740	0.0390	0.0230
BL00794	116.72	117.22	0.3600	0.0090	0.0300
BL00795	117.22	118.00	0.0200	0.0310	0.0040
BL00796	118.00	119.00	0.1300	0.0420	0.0120
BL00797	119.00	120.00	0.0580	0.0230	0.0070
BL00798	120.00	121.00	0.0490	0.0130	0.0070
BL00799	121.00	122.00	0.0320	0.0080	0.0060
BL00801	122.00	123.00	0.0360	0.0080	0.0060
BL00802	123.00	124.00	0.0360	0.0060	0.0060
BL00803	124.00	125.00	0.0600	0.0180	0.0080
BL00804	125.00	126.00	0.0450	0.0140	0.0060
BL00805	126.00	127.00	0.0010	0.0050	0.0020
BL00806	127.00	128.00	0.0010	0.0060	0.0030
BL00807	128.00	129.00	0.0010	0.0070	0.0020
BL00808	129.00	130.00	0.0005	0.0070	0.0030
BL00809	130.95	131.25	0.0200	0.0230	0.0040
BL00811	131.25	132.10	0.0570	0.0290	0.0020
BL00812	132.10	132.40	0.5880	0.1860	0.0430
BL00813	132.40	132.90	0.0040	0.0100	0.0030
BL00814	132.90	133.90	0.0070	0.0160	0.0030
BL00848	173.35	174.35	0.0050	0.0025	0.0020
BL00849	174.35	175.35	0.0050	0.0025	0.0020
BL00850	175.35	176.35	0.0120	0.0060	0.0040
BL00851	176.35	177.20	0.0160	0.0120	0.0030
BL00852	177.20	178.10	0.0380	0.0330	0.0050
BL00853	178.10	179.10	0.0100	0.0025	0.0030
BL00854	179.10	180.10	0.0040	0.0025	0.0020
BL00855	180.10	181.10	0.0040	0.0025	0.0020